

## ABRASIVE CHARGES for R191

Code : R191P



- A sample of aggregate is rolled with charges in a rotating drum.
- Those charges are steel spheres or ball bearings with varying diameters based on the applicable standards.

### STANDARDS

ASTM C131 • ASTM C535 • EN 1097-2

### TECHNICAL SPECIFICATIONS

|          |              |           |              |              |
|----------|--------------|-----------|--------------|--------------|
| Code     | R 191 P001 H |           | R 191 P002 H | Code         |
| Standard | ASTM C131    |           | EN 1097-2    | R 191 X00X T |
| Diameter | Ø 47.6 mm    | Ø 46.0 mm | Ø 47.6 mm    | R 191 X00X K |

|          |       |       |       |              |
|----------|-------|-------|-------|--------------|
| Weight   | 440 g | 400 g | 440 g | R 191 P001 H |
| Quantity | 5     | 7     | 11    | R 191 P002 H |

### ORDERING INFORMATION

| Code         | Item                                    |
|--------------|---|
| R 191 X00X T | LOS ANGELES ABRASION TESTER             |
| R 191 X00X K | LOS ANGELES ABRASION TESTER [60 Hz]     |
| R 191 P001 H | ABRASIVE CHARGES for AG-191 - ASTM      |
| R 191 P002 H | ABRASIVE CHARGES for AG-191 - EN        |
| R 191 P004 H | ABRASIVE CHARGE - Ø 46.0 mm / 400 g     |
| R 191 P005 H | ABRASIVE CHARGE - Ø 47.6 mm / 440 g     |
| R 191 P003 H | SOUND PROOF / SAFETY CABINET for AG-191 |